

Technical Bulletin

ElasTechs 2740

DESCRIPTION

ElasTechs 2740 is a formulated one piece sizing agent designed for application on 100% polyester spun yarn woven on high speed looms. The product is designed to be used alone – requiring no additives. additives.

ElasTechs 2740 is an outstanding film forming agent making it ideal for sizing spun polyester yarns.

BENEFITS

ElasTechs 2740 has the following beneficial characteristics.

- Premium One Piece Product
- Designed for Spun Polyester Yarn
- Improves Weaving Performance
- Reduces Size and Fiber Shedding

TYPICAL PROPERTIES

Color	White
Texture	Powder
pH	About 6.0
Moisture	About 10.0%
Solubility	Dispersible

PREPARATION

ElasTechs 2740 requires cooking prior to use. Add calculated quantity to cold starting water followed by other ingredients. Increase the liquor temperature to boiling and hold for about 30 – 45 minutes. The sizing solution is now ready for use.

APPLICATION

ElasTechs 2740 may be applied at 10 – 12% add on depending upon the degree of difficulty of the weave.

REMOVAL

ElasTechs 2740 is easily removed by conventional desizing methods.

ElasTechs 2740 should be stored in a cool, dry and well-ventilated area.

HANDLING

Follow good industrial hygiene when handling **ElasTechs 2740**. Please refer to the Material Safety Data Sheet for details.

PACKAGING

ElasTechs 2740 is available in 50 lbs and 25 kgs multi wall kraft-bags loaded on pallets with trays, caps and stretch wrapped.

Date Established: 09/22/09
Date Revised:

The information contained in this bulletin is to the best of our knowledge, true and accurate. This information is offered as a general guide to facilitate experimentation as to its suitability to the local plant environment, but neither an express or implied warranty of merchantability of the above mentioned product for particular use. American Textile, LLC make no guarantee of results and assume no obligation or liability whatsoever in connection with this information. This information is neither a license to operate under, nor is it intended to suggest infringement of any patent rights.